



Arch Aluminum & Glass Co., Inc.

Performance Data

Glazing Contractor: All Glass

Make-Up: One Inch Insulated Unit

Outboard Lite: 1/4" Gray Reflective #2

Airspace: 1/2" Mill

Inboard Lite: 1/4" Clear

Visible Transmittance	17%
Solar Transmittance	20%
UV Transmittance	6%
Visible Light Reflectance-outside	10%
Solar Reflectance	9%
Winter Nighttime U-Factor	0.47
Summer Daytime U-Factor	0.50
Shading Coefficient	0.39
Solar Heat Gain Coefficient	0.33

Performance data is based on representative samples of factory production.
All tabulated data are based on NFRC methodology using LBL's Windows 5.2 software.

2030 N.W Progress Parkway
Jackson, MS. 39213
800-815-5658 (Phone)
601-713-0302 (Fax)