



Arch Aluminum & Glass Co., Inc.

Performance Data

Glazing Contractor: All Glass

Make-Up: 1" Inch Insulated Unit
Outboard Lite: 1/4" Clear
Airspace: 1/2" Mill
Inboard Lite: 1/4" Clear

Visible Transmittance	79%
Solar Transmittance	61%
UV Transmittance	50%
Visible Light Reflectance	15%
Solar Reflectance	12%
Winter Nighttime U-Factor	0.47
Summer Daytime U-Factor	0.50
Shading Coefficient	0.81
Solar Heat Gain Coefficient	0.70

Performance data is based on representative samples of factory production.
All tabulated data are based on NFRC methodology using LBL's Windows 5.2 software.

2030 N.W Progress Parkway
Jackson, MS. 39213
800-815-5658 (Phone)
601-713-0302 (Fax)